

BauderTHERMOPLAN SK 18

Technical data sheet

Type of application	FPO/TPO waterproofing membrane for adhered laying self-adhesive with or without ballast	
Surface	Top	silver grey similar RAL 7001
	Bottom	Special fleece with self-adhesive layer
Reinforcement	Type	Special glass fibre – glass fabric
Article number	6648 1150	

Characteristic	Test method	Value
Visible defects	EN 1850-2	no visible defects
Length	EN 1848-2	20 m (-0/+5%)
Width	EN 1848-2	1,5 m (-0,5/+1%)
Straightness	EN 1848-2	< 50 mm
Flatness	EN 1848-2	< 10 mm
Mass per unit area	EN 1849-2	2,3 kg/m ² (-5/+10%)
Effective thickness	EN 1849-2	1,8 mm (-5/+10%) +1mm fleece/self-adhesive film
Water tightness	EN 1928 Method B	passed
External fire performance	CEN/TS 1187	npd
Reaction to fire	EN 13501-1	class E according EN 13501-1
Joint peel resistance	EN 12316-2	≥ 300 N
Joint shear resistance	EN 12317-2	> 400 N
Tensile force	md	EN 12311-2 A
	cd	EN 12311-2 A
Elongation at break	md	EN 12311-2 A
	cd	EN 12311-2 A
Resistance to impact	hard surface	EN 12691
	soft surface	EN 12691
Resistance to static load	hard surface	EN 12730
	soft surface	EN 12730
Tear resistance	EN 12310-2	> 300 N
Resistance to root penetration	EN 13948	in test
Dimensional stability	EN 1107-2	< 0,3 %
Foldability at low temperature	EN 495-5	≤ -40 °C
UV exposure (> 5000h)	EN 1297	passed
Durability Watertightness after artificial ageing	EN 1296 acc. EN 1928 (Method B 24h/60kpa)	passed
Durability Watertightness after exposure to chemicals	EN 1847 acc. EN 1928 (Method B 24h/60kpa)	passed
Hail resistance	hard surface	EN 13583
	soft surface	EN 13583
Water vapour properties ¹⁾	EN 1931	150000 (±30%)
Exposure to bitumen	EN 1548	passed
Nail Shaft test	EN 12310-1	npd

¹⁾The characteristic meant is the moisture resistance factor μ .



Identification number of the certification body: 0800

09

CPR – 51213; EN 13956 / CPR – 51214; EN 13967

Unique Code: BauderTHERMOPLAN SK 18 - 03