

# Bauder Super AL-E PLUS

## Technical Data Sheet


Type of application:	<b>Elastomer bitumen torch-on membrane as vapour barrier</b>		
Surface	top:	<b>Natural slate with foil strip in the middle</b>	
	bottom:	<b>Foil</b>	
Reinforcement	type:	<b>Aluminium polyester combination + glass fleece</b>	
Article number	<b>1332 0000</b>		

Characteristic	Test method	Unit	Value
Length	DIN EN 1848-1	m	5.0
Width	DIN EN 1848-1	m	1.0
Thickness	DIN EN 1849-1	mm	3.7
Flexibility at low temperature	DIN EN 1109	°C	≤ -20
Flow resistance at elevated temperature	DIN EN 1110	°C	≥ +70
Tensile properties: max. tensile force	DIN EN 12311-1	N / 50 mm	length: ≥ 400      transverse: ≥ 400
Tensile properties: elongation	DIN EN 12311-1	%	length: ≥ 2      transverse: ≥ 2
Straightness	DIN EN 1848-1	mm / 10m	≤ 20
Watertightness type A and T	DIN EN 1928 Verf. B	-	passed
Water vapour transmission properties (sd-value)	DIN EN 1931	m	≥ 1500
Reaction to fire	DIN EN ISO11925-2	-	class E according to DIN EN 13501-1
External fire performance	DIN EN ENV 1187	-	B <sub>ROOF</sub> (t1)*
Visible defects	DIN EN 1850-1	-	no visible defects
Peel resistance of joint	DIN EN 12316-1	N / 50 mm	nvs
Shear resistance of joint	DIN EN 12317-1	N / 50 mm	nvs
Resistance to impact	DIN EN 12691	mm	nvs
Resistance to static loading	DIN EN 12730	kg	nvs
Dimensional stability	DIN EN 1107-1	%	nvs
Artificial ageing DIN EN 1296	DIN EN 1109	°C	nvs
	DIN EN 1110	°C	

nvs = no value specific

\* tested in system

The declared values are determined statistically and are subject to tolerances.



# Bauder Super AL-E PLUS

## Product Information

Type of application:		<b>Elastomer bitumen torch-on membrane as vapour barrier</b>
Surface	top:	<b>Natural slate with foil strip in the middle</b>
	bottom:	<b>Foil</b>
Reinforcement	type and weight:	<b>Aluminium polyester combination + glass fleece</b>
Article number		<b>1332 0000</b>

<b>Product description</b>	Torchable elastomer bitumen membrane with reinforcement from aluminium polyester combination and glass fleece.
<b>Field of application</b>	Vapour barrier membrane for application under different thermal insulations.
<b>Service description</b>	Bauder Super AL-E PLUS is welded full-surface or punctually on the substructure or can be loose-laid according to specification of the construction supervision. Joint and lap area are welded with 8 -10 cm wide overlap. Place joints and laps shifted.
<b>Storage</b>	Store Bauder bitumen membranes vertically and protected against UV-radiation, humidity and heat. In cold season the rolls possibly have to be tempered before.
<b>Waste handling</b>	Bitumen waste can be disposed with an ordinary public waste or similar trade waste (European waste catalogue EWC number 170302 „asphalt-tarless“)